



Composition: 100% Polyester

Width: 138 cm

Weight: 430 gsm

Wyzenbeek Abrasion (ASTM D4157): warp 15,000 Rubs, weft 15,000 rubs

Color Fastness to Wet /Dry Crocking (AATCC 8): Wet 4.5, Dry 4.5

Breaking (Tensile) Strength: ASTM D5034: Warp: 109.2 lbf, weft: 103.6 lbf

Seam slippage: ASTM D4034-92: warp 43.1 lbf, weft 48.2 lbf

Tearing Strength ASTM D2261; Tongue: Warp 18.9 lbf, Weft 36.7 lbf

Dynamic Seam Fatigue (ASTM D4033,): Warp-to-Warp Seam 2 mm,

Weft-to-Weft Seam 1.5mm, Warp-to-Weft Seam 2 mm

Pilling Resistance ASTM D3511: 3.5

Dry clean / Gentle machine wash

1



2



3



4



5



6



7



8



9



10



11



12

